

# ROCK



Italiano	English	Français	Deutsch		
Pavimentazione agugliata	Needle punched carpet	Tapis aiguillete	Nadelvlies Teppichboden	ISO 2424	ROCK
Dati di fabbricazione	Technical Data	Caracteristiques techniques	Technische Daten		
Dimensione rotoli standard	Standard rolls dimensions	Dimensions standard des rouleaux	Rollen abmessungen	ISO 3018	30 m x 2 m
Composizione della fibra dello strato di utilizzo	Fiber composition of use surface	Composition fibreuse de la couche d'usage	Faserzusammensetzung der Nutschicht	Dir. 96/73 CE	100% PA
Composizione supporto	Back layer	Couche d'envers	Traeger		100% sintetico
Tipo di dorso	Backing	Enduction d'envers	Rücken	ISO 2424	Latex
Massa areica totale	Total mass per unit area	Masse totale par unité de surface	Flaechengewicht	ISO 8543	1.250 gr/m <sup>2</sup>
Spessore totale	Total thickness	Épaisseur totale	Gesamtdicke	ISO 1765	5,2 mm
Carica elettrostatica	Body voltage	Essai du marcheur	Koerperspannung	EN 1815	< 2,0 Kv
Traffico	Suitability	Professionel moyen	Beanspruchungsbereich	EN 1307	Classe 4
Assorbimento acustico	Sound absorption	Performance acoustique	Trittschalldämmung	ISO 140/8	20 dB
Comportamento alla fiamma	Flammability	Reaction au feu	Brandverhalten	EN 13501-1 D.M. 26.06.84	Bfl - s1 Classe 1
Pavimentazione agugliata	Needle punched carpet	Tapis aiguillete	Nadelvlies Teppichboden	ISO 2424	QUADROTTA ROCK
Dati di fabbricazione	Technical Data	Caracteristiques techniques	Technische Daten		
Scatola	Box	Boîte	Karton	ISO 3018	4 m <sup>2</sup>
Composizione della fibra dello strato di utilizzo	Fiber composition of use surface	Composition fibreuse de la couche d'usage	Faserzusammensetzung der Nutschicht	Dir. 96/73 CE	50% PA + 50% PP
Tipo di dorso	Backing	Enduction d'envers	Rücken	ISO 2424	Bitumen
Massa areica totale	Total mass per unit area	Masse totale par unité de surface	Flaechengewicht	ISO 8543	4.200 gr/m <sup>2</sup>
Spessore totale	Total thickness	Épaisseur totale	Gesamtdicke	ISO 1765	6,5 mm
Comportamento alla fiamma	Flammability	Reaction au feu	Brandverhalten	EN 13501-1 D.M. 26.06.84	Cfl - s1 Classe 1
Pavimentazione agugliata	Needle punched carpet	Tapis aiguillete	Nadelvlies Teppichboden	ISO 2424	ROCK CONDUTTIVO
Resistenza	Resistibility	Resistivité	Leitungswiderstand	ISO 10965	10 <sup>8</sup> Ohm
Impiego Uffici commerciali e amministrativi Grandi magazzini Centri sociali e sportivi Cinema e teatri	Uses Offices Computer rooms Stores Cinemas and theatres Sport clubs	Utilisation Bureaux informatiques Magasins Cinémas et théâtres Sport clubs	Verwendungsbereich Grobraumbüros Computerräume Kaufhäuser Kinos und Theater Sport Clubs		rev. 2 01/04

PAVITEX

Strapazierwert				Komfortwert			
en	stark	normal	gering	einfach	gut	hoch	luxuriös

