



## Report 6551

### Classification Report on Burning Behaviour

#### Applicant

VIGANO PAVITEX S.p.A.  
Via Carlinga 35  
24035 Curno (BG)  
ITALIEN

#### Reference

Ing. Alberto VIGANO

#### Application

Classification of burning behaviour according to EN 13501-1.

#### Test Material

"CONTRACT TILES BITUMEN FR"

Material used in testing was anonymized for laboratory purposes. A detailed sample list is contained in the report.

#### Issuing and Signatures

Number of pages contained: 6

Original Issue / Vienna 2011-04-15 / Rm/AM/KK 253  
Translation

Authorised for Institute  
DI (FH) Angelika Hönecke

Technology  
Ing. Judith Pointner ☎ 28 / pointner@oeti.at





## Contents

1	Order.....	2
1.1	Chronology.....	2
2	Introduction.....	3
3	Details of classified building product.....	3
3.1	General.....	3
3.2	Description of the building product.....	3
4	Test reports and test results for the proof of the classification.....	3
4.1	Test report.....	3
4.2	Test results.....	4
5	Classification and field of application.....	4
5.1	Reference for classification.....	4
5.2	Classification.....	4
5.3	Field of application.....	4
6	Limitations.....	4
6.1	Validity.....	4
6.2	Notice.....	5
7	Äquivalenzbeurteilung zur Verwendung in Österreich.....	5
8	Remarks.....	6

## 1 Order

### 1.1 Chronology

<i>Date</i>	<i>Received</i>	<i>Order</i>
2011-02-15	2011-02-15	Classification of burning behaviour according to EN 13501-1.



## 2 Introduction

This classification report defines the classification assigned to the building product group "**CONTRACT TILES BITUMEN FR**" in accordance with the test methods fixed in EN 13501-1:2009.

## 3 Details of classified building product

### 3.1 General

The building product group "**CONTRACT TILES BITUMEN FR**" is defined as flooring, the classification is valid for the end use application described under point 5.3.

### 3.2 Description of the building product

The building product group "**CONTRACT TILES BITUMEN FR**" is defined according EN 14041 as following:

Type	textile floor covering
Dimensions	tiles
Manufacturing technique	needle floor covering, single layer
Surface structure	plane
Backing	coated backing (Bitumen) with non-woven coated
Pile material	100 % polypropylene
Total weight	4200 g/m <sup>2</sup>
Total thickness	7,5 mm

The applicant of this classification report guarantees the observance of the instructions for building product groups according EN 14041 as well as the observance of the instructions of the product specification according to EN 1470.

The following articles are part of the building product group "**CONTRACT TILES BITUMEN FR**".

Article	Total weight [g/m <sup>2</sup> ]	Total thickness [mm]
Metro Tiles Bitumen	4200	7,5

## 4 Test reports and test results for the proof of the classification

### 4.1 Test report

Laboratory	ÖTI
Test report number	65550
Date of issue	2011-04-15
Applicant	VIGANO PAVITEX S.p.A.
Test methods	EN ISO 11925-2 und EN ISO 9239-1



## 4.2 Test results

	Test results (Mean Value)	Number of tests
<b>Ignitability, EN ISO 11925-2</b> Flame spread $\leq$ 150 mm	<b>yes</b>	6
<b>Burning behaviour, EN ISO 9239-1</b> Critical radiant flux	<b>8,1 kW/m<sup>2</sup></b>	3
Integral of smoke obscuration	<b>357 %·min</b>	3

## 5 Classification and field of application

### 5.1 Reference for classification

This classification has been carried out in accordance with EN 13501-1:2009.

### 5.2 Classification

Due to the results of the tests carried out, the building product group "**CONTRACT TILES BITUMEN FR**" can be classified as following.

Burning behaviour	Smoke emission
<b>B<sub>fl</sub></b>	<b>s1</b>
<b>Classification</b>	
<b>B<sub>fl</sub>-s1</b>	

### 5.3 Field of application

The classification is valid for the building product described in point 3 under the following end use conditions.

Application	Horizontal laid floor covering in form of rolls
Subfloors	Not burnable subfloors of euroclass A1 <sub>fl</sub> or A2 <sub>fl</sub> with a density of at least 1350 kg/m <sup>3</sup> .
Installation	unglued and glued/adhered

## 6 Limitations

### 6.1 Validity

The report stays valid as long as the products are produced in unchanged condition; this is in the responsibility of the manufacturer.



## 6.2 Notice

This classification document does not represent type permission or certifying the product.

If a building product should be CE marked according to system 3 of the attestation of conformity systems, the classification stated with this report is suitable as a basis for the declaration of the producer according to the attestation of conformity system 3, together with a CE marking in the context of the directive relating to construction products.

If the manufacturer plans a CE marking in connection with conformity system 3, he has to give an explanation, which has to be attached to the relevant documents. This explanation confirms, that there are no the specific materials, production processes or procedures (e.g. no additives of flame retarding materials, delimitation of organic components or additions of fillers), which are improving the burning behaviour to reach the obtained fire classification. As a consequence from this, the manufacturer drew the conclusion that the system 3 of the attestation of conformity systems is appropriate.

The testing laboratory therefore has played no role in the sampling procedure, although the testing laboratory keeps appropriate references from the manufacturer ready, in order to pursue the examined samples.

## 7 Äquivalenzbeurteilung zur Verwendung in Österreich

Unter Zugrundlegung der Anforderungsbedingungen ist eine eindeutige Zuordnung der ehemaligen österreichischen Brandklassifizierung zu einer europäischen Klasse nicht immer möglich und bedarf umfassender Einstufungserfahrung.

Die vorliegende Äquivalenzbeurteilung soll als Hilfestellung verstanden werden die zeigen soll, in welche europäische Klasse ein Bauprodukt fallen kann, das gemäß österreichischen Normen eingestuft wurde und umgekehrt.

Einstufung gemäß EN 13501-1	Anforderungen aus landesgesetzlichen Bestimmungen	
A <sub>fl</sub>	nichtbrennbar, schwachqualmend	A
A <sub>fl-s1</sub>		
B <sub>fl-s1</sub>	schwerbrennbar, schwachqualmend	B1
C <sub>fl-s1</sub>		
D <sub>fl-s1</sub>	normalbrennbar, schwachqualmend	B2
A <sub>fl-s2</sub>		
B <sub>fl-s2</sub>		
C <sub>fl-s2</sub>		
D <sub>fl-s2</sub>		
E <sub>fl</sub>		
F <sub>fl</sub> <sup>1)</sup>	leichtbrennbar	B3

<sup>1)</sup> Es wird darauf hingewiesen, dass die Europäische Klasse F auch die Tatsache ausdrücken kann, dass noch gar keine Klassifizierung stattgefunden hat.



## 8 Remarks

### Sample Material

Without explicit written other agreement testing is destructive and the sample material is transferred to the property of ÖTI, which is entitled to freely decide on storage and disposal.

### Quality management and accreditations

All tests and services are performed under a quality management system according to EN ISO 17025.

ÖTI is accredited by several organisations for various tests offered. It also is a Notified Body for several directives with the registration number 0534 (see <http://ec.europa.eu/enterprise/newapproach/nando/>). The accreditation by the Federal Ministry of Economy, Family and Youth as testing laboratory was repeated under reference 92.714/0560-I/12/2009 (Individual accredited test procedures are marked with the federal laboratory logo), the accreditation for testing and inspection of construction products was given by the OIB (Austrian Institute of Construction Engineering). Details and other accreditations are given on request and can be found on [www.oeti.at](http://www.oeti.at).

### Issuance

The valid first issue is done in paper and has single-handed signatures. For reference purposes and filing an unsigned electronic duplicate can be delivered in pdf format. Duplicates and translations will be marked accordingly on the cover sheet.

### Copyright und Usage Notes

It is pointed out, that any alterations, amendments or falsifications of reports not authorized by the issuer of the report will be prosecuted as civil and criminal offences; this especially to the appropriate requirements of ABGB, UrhG, UWG and criminal law and their respective international equivalents.

Reports are protected under international copyright laws. Written consent of the ÖTI is required for publications (also in excerpt) and reference to tests for public relation purposes. Reports may only be reproduced in full length.